

## Balanced net for structural reinforcement data sheet

### Code # C210N

Characteristics		
	Nominal	Tolerance
Mass per unit of area (g/m <sup>2</sup> )	236	± 5%
Weave	0/90 scrim	
Laminate thickness (mm)	0,25*	n/a

Warp – Weft ratio		
	Warp	Weft
Fiber description	12K carbon fiber + thermoplastic	12K carbon fiber + thermoplastic
Weight distribution (g/mq)	104 + 14	104 + 14
Weight distribution (%)	44 + 6	44 + 6

(\*) Theoretical thickness of compressed epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

