

## SG 715

### Epoxy Gel-coat

#### Properties

The SG 715 / SD 802 is a two component epoxy gel coat that is very easy to spread with brush or roller, and hardens practically without shrinking at room temperature. It gives a hard surface with resistance to abrasion and is easy to polish. Its thixotropic but nevertheless supple consistency makes the resin/hardener mixture easy to apply without bubbles with a short haired brush in a layer thickness of 1-3 mm.

The SG 715 / SD 802 system does not run down at edges, corners and vertical surfaces. Allow to gel before applying a second coat. To avoid the risk of delamination, lamination must begin with no delay as soon as the gel coat is no longer tacky. If needed, the system can be made thinner by mixing together with other epoxy systems or epoxy solvent.

#### Physical properties

Reference	Definition	Appearance	Viscosity Cps at 20 °C	Viscosity Cps at 25°C	Density g/ml at 20°C
SG 715	Resin	White or black gel	Thixotropic	Thixo.gel	1.16 ± 0.05
SD 802	Hardener	Colourless liquid	33 ± 5	29 ± 5	0.96 ± 0.01
EP 960	Thinner	Colourless liquid	2 ± 0.5	/	0.789

#### Mixing proportions

For application with a roller/brush:

**White SG 715 / SD 802 / EP 960**                                      **100 g / 27 g / 0 to 6 g**

For application with a spray gun: the R/H mixture to be diluted to a maximum of 20% by weight of EP 960 thinner

**White SG 715 / SD 802 / EP 960**                                      **100 g / 27 g / 27 g maximum**

#### Reactivity of undiluted mix

Ambient temperature:	<b>at 20°C</b>	<b>at 25°C</b>
Pot-life measured on 150 g of mix/Exothermic temperature:	29' / 160° C	21' / 170° C
Time to reach 50°C for 150 g mix:	17'	12'
Time to be dry to touch in film:	2 h 20'	1 h 45'
Hard film after:	6 h	4 h

#### Conditions for application

18 °C < Temperature of the substrate < 50 °C  
Hygrometry < 80%

### Release agent

Check compatibility with **SG 715** (resistance to or facility of removal from mould...) by making a preliminary test, specially if the gelcoat is used diluted.

Wax 103: for curing at below 50° C and undiluted gel coat

Cirex DE 68: for curing at above 50° C and diluted gel coat

### Processing

Brush/roller for lacquer

Thinning: 0 to 5% of weight of mix

Pneumatic spray gun: Carefully mix the **SG 715** and **SD 802** resin, and leave to develop for five minutes.

Thin with 20% maximum of EP 960: for 100 g of SG 715 / 802 mix, add 20 g of EP 960 thinner. Mix carefully.

Spray in thin coats 40 cm from the substrate. Wait 5' between each coat.

Allow the gel coat to gel before applying the second coat or laminating. The gel coat must be tacky (still sticky to the finger) to avoid any risk of delamination.

### Equipment

Brush/roller

### Lamination

Lamination must begin as soon as the **SG 715** is no longer tacky.

### Post-curing

If possible, carry out post-curing in the mould so as to limit marking of fibres.

12 hours @ 20°C + 24 hours @ 40°C

or 12 hours @ 20°C + 8 hours @ 60°C




### Thermal stability

Tg1=90° C after 24 hours at ambient temperature + 8 hours at 60° C

### Cleaning

EP 960 thinner, methyl ethyl ketone (MEK), solvent for epoxide paints.

## Toxicity / Labelling

Products	Labels		Risk Classification
<b>SG 715</b>		Xn: Harmful	R 36/38: Irritant for eyes and skin R 51/53: Toxic for aquatic organisms, may have harmful effects, in the long term, on the aquatic environment R 43: May cause sensitisation through skin
<b>SD 802</b>		C: Corrosive	R 21/22: Harmful if swallowed or if there is skin contact R 34: Causes burning R 43: May cause sensitisation through skin contact
<b>EP 960</b>		Flammable	R 11, 23/25

(EEC Classification in accordance with Annex 1 of EEC Directive 67 / 548)

We do not bear responsibility for any written or verbal information which may be given by us in the course of our technical assistance or tests which we have carried out. We advise users of SICOMIN epoxy systems to check, by means of practical tests, whether our products are suitable for the processes and uses envisaged. The use, implementation and transformation of the products supplied is outside our control and falls within your sole responsibility.

If, however, we were to bear any responsibility, this would be limited, for the purposes of any damages, to the value of the goods supplied by us and set in operation by you. We guarantee the impeccable quality of our products within the context of our general conditions of sale and delivery.