

## Woven fabric data sheet

### Code # G1125Z

Characteristics		
	Nominal	Tolerance
Mass per unit of area (gr/sqm)	1125	± 5%
Weave	3D-non crimp	
Laminate thickness (mm)	0,90*	± 15%

Warp – Weft ratio		
	Warp	Weft
Fiber description	Primary: E Glass fiber 1100 tex Secondary (Z direction): Polyester fiber 16,66 tex	E Glass fiber (2x) 735 tex
Thread count (ends/cm)	4,6	8,4
Weight distribution (g/mq)	517,5	607,5
Weight distribution (%)	46	54

(\*) Theoretical thickness of compressed epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

