

## Balanced woven fabric data sheet

## Code # CP210Tb

Characteristics				
	Nominal	Tolerance		
Mass per unit of area (gr/sqm	210	± 5%		
Weave	Twill 2X2			
Laminate thickness (mm)	0,21	± 15%		

Warp – Weft ratio				
		Warp	Weft	
Fiber description		3K carbon fiber 200tex	Polyester fiber (blue) -1100dtex	
Thread count	(ends/cm)	4,80	10,00	
Weight distribution	(gr/sqm)	98	110	
Weight distribution	(%)	47	53	
Total weight rate	(%)	47	53	

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

Head office: Fibremax Ltd 35 Grafton Way, W1T 5DB London, UK