



Balanced woven fabric data sheet

Code # CP260Tr

Characteristics		
	Nominal	Tolerance
Mass per unit of area (gr/sqm)	257	± 5%
Weave	Twill 2X2	
Laminate thickness (mm)	0,25	± 5%

Warp – Weft ratio		
	Warp	Weft
Fiber description	HS carbon fiber TR30S 3K	HS carbon fiber TR30S 3K Polyester fiber (red) -122
Thread count (ends/cm)	7	Carbon 3,8 Polyester 3,8
Weight distribution (gr/sqm)	140	Carbon 75 Polyester 42
Weight distribution (%)	54	Carbon 29 Polyester 16
Total weight rate (%)	54	46

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

