

## Balanced woven fabric data sheet

### Code # K300T2

Characteristics		
	Nominal	Tolerance
Mass per unit of area (gr/sqm)	300	± 5%
Weave	Twill 2x2	
Laminate thickness (mm)	0,42*	± 15%

Warp – Weft ratio		
	Warp	Weft
Fiber description	Aramid fiber 2200 3220 dtex	Aramid fiber 2200 3220 dtex
Thread count (ends/cm)	6,7	6,7
Weight distribution (g/mq)	150	150
Weight distribution (%)	50	50

(\*) Theoretical thickness of compressed epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

