

## Balanced aluminized woven fabric data sheet

## Code # GA290T2

| Characteristics       |          |           |           |  |
|-----------------------|----------|-----------|-----------|--|
|                       |          | Nominal   | Tolerance |  |
| Mass per unit of area | (gr/sqm) | 290       | ± 5%      |  |
| Weave                 |          | Twill 2X2 |           |  |
| Laminate thickness    |          | 0.23*     | ± 15%     |  |

| Warp – Weft ratio   |           |                      |                    |  |
|---------------------|-----------|----------------------|--------------------|--|
|                     |           | Warp                 | Weft               |  |
| Fiber description   |           | 3 X EC9 68 tex fiber | EC11 204 tex fiber |  |
| Thread count        | (ends/cm) | 7                    | 7                  |  |
| Weight distribution | (g/mq)    | 145                  | 145                |  |
| Weight distribution | (%)       | 50                   | 50                 |  |

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

