



PYROFIL™ TR50S 6K

Typical Fiber Properties

Tow Tensile	Strength	711 4,900	ksi MPa	ASTM D4018
	Modulus	34 235	msi GPa	
Typical Density		0.066 1.82	lb.in ³ g/cm ³	ASTM D4018
Typical Yield	6K	1,240 400	yds/lb mg/m	ASTM D4018

5900 88th Street
 Sacramento, CA
 95828, USA
 Tel: 916.386.1733
 Fax: 916.383.7668
 Web: www.grafil.com



ISO 9001:2008
 FM 56416

03/2010

6, Orchard Court
 Binley Business Park
 Harry Weston Road
 Binley, Coventry CV3 2TQ UK
 Tel: +44 (0) 2476 447272
 Fax: +44 (0) 2476 449565